

DATA SHEET

MIPOX

MIPOX two-component decorative coating based on polymeric quartz powder and epoxy resin in aqueous dispersion, allows to create a continuous, resistant and long-lasting coating. With great mechanical and chemical resistance, it is suitable for covering and decorating horizontal and vertical parameters, indoors and outdoors, leaving a continuous covering, without joints and without the need to remove the original surface. It is already pigmented on the RAL color table.

COMPOSITION

MIPOX COMPONENT A - Polymeric quartz powder and epoxy resin

Format 10 Kg

MIPOX COMPONENT B Catalyst

Format 1 Kg

GRANULOMETRY

MIPOX BASE XL 0.4 mm

MIPOX Medium 0.2 mm

MIPOX Fine 0.06 mm

SPECIFICATIONS

- o Mechanical resistance (EN 1015-11): Compression 28 days > 45 N / mm²
- o Dry dimensions: Base 0.4 mm - Floor 0.2 mm - Wall 0.06 mm
- o Application thickness: 1-2 mm per layer
- o PH rank: 12 PH

PRODUCT CODE

MIPOX BASE: RE4005

Medium MIPOX: RE4006

MIPOX Fine: RE4007



INSTRUCTIONS FOR USE RECRYTE MIPOX

It is applied with a spatula

1. Apply to clean, dry surfaces free from dust, grease and mold. Old paints must be scratched and cleaned thoroughly to ensure perfect adhesion of the product.
2. Apply a layer of adhesion with RECRYTE PRIMER UNION and let it dry for at least 1 hour, maximum 24 hours. Apply at temperatures between 12 ° - 25 ° C with humidity below 80%
3. The product is pre-dosed in MIPOX COMPONENT A - MIPOX COMPONENT B Add component B to component A and mix thoroughly in the same container, until a mixture is as homogeneous as possible. Add water if it thickens or even if you want a less viscous mixture.
4. Apply one or two coats of MIPOX BASE, allowing it to dry for 6 to 8 hours, depending on the ambient temperature.
5. Regularize the surface to be treated by sanding with 40/80 sandpaper
6. Spread two coats of RECRYTE MIPOX Medium or RECRYTE MIPOX fine with a spatula at intervals of 6 to 8 hours, depending on the temperature. Once the first coat has dried, apply the second coat
7. Once dry, wipe with 80 or thicker sandpaper to remove imperfections.
8. Apply two coats of RECRYTE FINISH WT varnish
9. Leave to dry for approximately 6 to 8 hours

STORAGE INSTRUCTIONS

Protect containers from extreme temperatures, direct sun exposure and frost, at temperatures between 5 ° and 25 ° during storage

Usage time is 6 months from production date, properly stored.

HYGIENE AND SAFETY

Keep out of reach of children.

Use in well-ventilated areas with personal protective equipment.

DISPOSAL AND ENVIRONMENT

Do not dispose of waste in sewers or water courses.

Empty containers must be disposed of in accordance with local / national legislation in force

